

Technical Bulletin

1 December 2019

Group numbers for wall and ceiling linings

According to the National Construction Code, volume 1, internal wall and ceiling linings within class 2 to 9 buildings must comply with specific fire hazard properties. A Group Number is the system used to classify materials proposed for these linings. This classification governs if and where the material can be used. The NCC deemed-to-satisfy provisions vary depending on the building class and application, but in all cases the Group Number must be 1,2 or 3.



Test standards and Fletcher Insulation products compliance:

AS 5637.1:2015 is the standard referenced for the determination of a Group number as stated in the NCC 2019 as a requirement.

Extract from NCC 2019:

- 4. Wall and ceiling linings
 - (a) A wall or ceiling lining system must comply with the group number specified in Table 3 and for buildings not fitted with a sprinkler system (other than a FPAA101D or FPAA101H system) complying with Specification E1.5 have:
 - (i) a *smoke growth rate index* not more than 100; or
 - (ii) an average specific extinction area less than 250m²/kg.
 - (b) A group number of a wall or ceiling lining and the **smoke growth rate index** or **average specific extinction area** must be determined in accordance with AS 5637.1.

According to the standard, an internal wall and ceiling lining material shall be assigned a Group number between 1 and 4 through below testings, with Group 1 being the best performer.

- through physical testing to AS ISO 9705:2003 (with the lining material covering three walls and the ceiling) or
- through small scale testing according to AS 3837 or ISO5660.1 where performance correlation has been proven and confident prediction to ISO9705 can be attained.

Fletcher Insulation has tested their products by physical testing to AS ISO 9705:2003 (with the lining material covering three walls and the ceiling) and/or AS3837 if applicable.

All products achieve either a Group 1 or Group 2 ratings:

Pink [®] Thermal Slab							
Facing option	Thickness mm	Density kg/m³	Material R-Value	Group number	SMOGRA _{RC} m²s² x 1000		
Sisalation [®] HD facing foil	13	32	R0.4		<100		
	25	32	R0.8				
	38	32	R1.2				
	50	32	R1.5	1			
	66	32	R2.0				
	75	32	R2.3				
	100	32	R3.0				
Sisalation [®] Black HD facing foil	13	32	R0.4		<100		
	25	32	R0.8				
	38	32	R1.2				
	50	32	R1.5	1			
	66	32	R2.0				
	75	32	R2.3				
	100	32	R3.0				
Pink [®] NoiseSTOP with a Duras	orb°face						
Durasorb°	13	32	R0.4		<100		
	25	32	R0.8				
	38	32	R1.2				
	50	32	R1.5	1			
	66	32	R2.0				
	75	32	R2.3				
	100	32	R3.0				

Technical Bulletin

Permastop Building Blanket								
Facing option	Thickness mm	Density kg/m³	Material R-Value	Group number	SMOGRA _{RC} m²s² x 1000			
Sisalation [®] LD facing foil	55	11.8	R1.3		<100			
	55	11.8	R1.3					
	75	10.9	R1.8					
	75	10.9	R1.8					
	90	11.8	R2.0	4				
	100	14.3	R2.3	1				
	100	14.3	R2.5					
	130	10.45	R3.0					
	130	12.5	R3.2					
	130	18	R3.6					
	55	11.8	R1.3		<100			
	75	10.9	R1.8					
	100	14.3	R2.3					
Sisalation [®] MD facing foil	100	14.3	R2.5	2				
	130	10.45	R3.0					
	130	12.5	R3.2					
	130	18	R3.6					
	55	11.8	R1.3		<100			
	75	10.9	R1.8					
	100	14.3	R2.3					
Sisalation [®] White MD facing foil	100	14.3	R2.5	2				
	130	10.45	R3.0					
	130	12.5	R3.2					
	130	18	R3.6					
Sisalation [®] HD facing foil	55	11.8	R1.3		<100			
	75	10.9	R1.8					
	100	14.3	R2.3					
	100	14.3	R2.5	2				
	130	10.45	R3.0					
	130	12.5	R3.2					
	130	18	R3.6					
	55	11.8	R1.3	1	<100			
	75	10.9	R1.8		<100			
Sisalation [®] Black HD facing foil	100	14.3	R2.3					
	100	14.3	R2.5					
	130	10.45	R3.0	2				
	130	12.5	R3.2					
	130	18	R3.6					

What group number is required for your project?

Based on the building class and location, wall and ceiling lining material must comply as per the below table and 4(a) as noted on page 1 of this technical bulletin and referenced from NCC 2019 Volume 1:

Table 3 wall and ceiling lining materials (material groups permitted)

Class of Building	Fire-isolated exits and fire control rooms	Public corridors	Specific areas	Other areas	
Class 2 or 3, Unsprinklered Excluding accommodation for the aged,	Walls	1	1, 2	1, 2, 3	1, 2, 3
people with disabilities and children	Ceilings	1	1, 2	1, 2, 3	1, 2, 3
Class 2 or 3, Sprinklered Excluding accommodation for the aged,	Walls	1	1, 2, 3	1, 2, 3	1, 2, 3
people with disabilities and children	Ceilings	1	1, 2, 3	1, 2, 3	1, 2, 3
Class 3 or 9a, Unsprinklered Accommodation for the aged, people with	Walls	1	1	1, 2	1, 2, 3
disabilities, children and <i>health care buildings</i>	Ceilings	1	1	1, 2	1, 2, 3
Class 3 or 9a, Sprinklered Accommodation for the aged, people with	Walls	1	1, 2	1, 2, 3	1, 2, 3
disabilities, children and <i>health care buildings</i>	Ceilings	1	1, 2	1, 2, 3	1, 2, 3
Class 5, 6, 7, 8 or 9b schools, Unsprinklered	Walls	1	1, 2	1, 2, 3	1, 2, 3
	Ceilings	1	1, 2	1, 2	1, 2, 3
Class 5, 6, 7, 8 or 9b schools, Sprinklered	Walls	1	1, 2, 3	1, 2, 3	1, 2, 3
	Ceilings	1	1, 2, 3	1, 2, 3	1, 2, 3
Class 9b other than schools, Unsprinklered	Walls	1	1	1, 2	1, 2, 3
	Ceilings	1	1	1, 2	1, 2, 3
Class 9b other than schools, Sprinklered	Walls	1	1, 2	1, 2, 3	1, 2, 3
	Ceilings	1	1, 2	1, 2, 3	1, 2, 3
Class 9c, Sprinklered	Walls	1	1	1, 2	1, 2, 3
	Ceilings	1	1	1, 2	1, 2, 3

© Fletcher Insulation Pty Limited 2019. Fletcher Insulation reserves the right to change product specifications without prior notification. Information in this publication and otherwise supplied to users as to the subject product is based on our general experience and is given in good faith, but because of the many particular factors which are outside our knowledge and control and affect the use of products, no warranty is given or is to be implied with respect to either such information or the product itself, in particular the suitability of the product for any particular purpose. The purchaser should independently determine the suitability of the product for the intended application. Unless otherwise stated all TM and ® are trademarks and registered trademarks of Fletcher Insulation Pty Limited ABN 72 001 175 355. TB03_Revision_0_Issuedate 131219.

For more information please email the Fletcher Insulation technical team at technical@insulation.com.au

