
Verosol

202 SilverScreen Performance 2%

Semi Transparent Metallised



The ultimate low-E solution for solar protection and light control

Features

- Part of the Verosol Core Collection metallised fabrics developed in Europe, to the highest quality standard
- Provides excellent vision out, and dramatically reduces heat and glare at the window independent of colour
- Excellent energy efficient solution, offering an unparalleled solar reflectance of 85%
- Lowest-E fabric providing excellent insulative properties
- Constructed from a hard wearing PVC coated fibreglass yarn and is inherently flame retardant
- Greenguard Gold, Global Green Tag BEPPVC Best Environmental Practice PVC, and Global GreenTag EPD
- Suitable for Roller Blinds, Roman Blinds and Panel Glides

Care Instructions

Verosol fabrics are anti-static and therefore dust repellent. For regular maintenance, use a soft feather duster or vacuum-clean with a soft brush in a low setting.

For more information or to create your next specification visit verosolspecifications.com.au or call 1800 721 404



Formaldehyde Free







202 SilverScreen Performance 2%

Semi Transparent Metallised

Fabric Density	Semi Transparent		Pattern	Natté 1x2
Composition	64% PVC / 36% Fibreglass	Formaldehyde Free	Anti-Static	Yes
Weight	400gsm ± 5%			
Thickness	0.46mm ± 5%			
Width	2800mm ± 50mm			
Colour Fastness	7 - 8 [ISO 105-B02]	•••••••••••••••••••••••••••••••••••••••		
Flame Retardancy	Ignitability index	0 Range [0-20]		
[AS/NZS 1530.3-1999]	Spread of flame index	0 Range [0-10]		
	Heat evolved index	0 Range [0-10]		
	Smoke developed index	4 Range [0-10]	•••••••••••••••••••••••••••••••••••••••	•••••••••••••••••••••••••••••••••••••••
[AS/NZS 3837-1998]	Classification Group 2	•••••		••••••
[International]	NFP 92503 Specification M1	BS 5867 Part 2 Type B NFPA 701	••••••	••••••
Aluminium Adhesion	ISO 2409 Classification 0		• • • • • • • • • • • • • • • • • • • •	•••••••••••••••••••••••••••••••••••••••
Certification	Greenguard Gold	Best Environmental Practice PVC	ISO 14001:2015	ISO 9001:2015
••••••	Formaldehyde Free	REACH	REACH RoHS2	HPD 2.1
Suitable Products	Roller Blinds	Roman Blinds	Panel Glides	
••••••				•••••••••••••••••••••••••••••••••••••••

Fabric colour code	0010	0020	0030	0060	0040	0050
Solar transmittance	3%	3%	3%	3%	3%	2%
Solar reflectance outside						
Solar absorptance	12%	12%	12%	12%	12%	13%
Luminous transmittance [VLT]						
UV transmittance	3%	3%	3%	3%	3%	2%
IR emissivity metal side [low-E]	0.03	0.03	0.03	0.03	0.03	0.03
IR emisivity colour side	0.878	0.878	0.878	0.878	0.878	0.878
Openness factor (nominal)	2%	2%	2%	2%	2%	2%

Glazing Type - Single 4mm Clear Glass

Visible light transmittance	4%	3%	3%	3%	3%	3%
G-value / Solar heat gain coefficient	15%	15%	15%	16%	15%	16%
Shading coefficient	17%	17%	17%	18%	18%	18%
U-value (W/m²K)	2.0	2.0	2.0	2.0	2.0	2.0
Glazing Type - High Performance Glazing						

Visible light transmittance	3%	2%	2%	3%	2%	2%
G-value / Solar heat gain coefficient	11.6%	12%	12%	12%	12%	12%
Shading coefficient	13%	14%	13%	14%	14%	14%
U-value (W/m²K)	0.7	0.7	0.7	0.7	0.7	0.7

Colour Range

0010 White	0020 Beige	0030 Light Grey	0060 Bronze	0040 Dark Grey	0050 Black

© Copyright 2022 Verosol Australia [ABN 36 006 221 003] Updated September 2023 Information supplied was current at time of printing. Please refer to Warranty Terms & Conditions at www.verosol.com.au for more information. All presented data calculated in WIS 3.0.1 (Advanced Windows Information System) with spectral data. Specifications and other data are based on information available at the time of preparation of this document and are subject to production tolerances and/or change without prior notice. Flame retardancy information is sourced from AWTA testing results [AS/XVEJ 51303.11999]. Please note that test results may vary slight/depending on fabric colour. [4mm Single Glass reference glazing A EN 14501], [High Performance Glazing reference glazing D EN 14501] according to EN 14500. Note: All colours are representative only, please request an A4 sample for accurate colour representation at www.verosol.com.au.