

**TECHNICAL DATA SHEET**

6 16.11.2015

Page 1 of 2

**TEKNOSEAL 4001-00**

V-joint sealer

TEKNOSEAL 4001, an aqueous product for the protection of V-joints and corner joints of new wood designated for exterior use such as windows and doors.

**TECHNICAL DATA**

Binder: Synthetic binder.

Volatile organic compound (VOC): See Safety Data Sheet.

Colour range: Colourless

**APPLICATION DETAILS**

Pre-treatment: The wood must be clean and free from wood dust and contamination. The moisture content of the wood should be approx. 13 % and should not exceed 15 %.

All softwood and non-durable hardwood for exterior use should either be vacuum impregnated (only softwood) or treated with a wood preservative.

Application: Is applied by caulking gun or plastic bottle with spray nozzle. Smooth with a putty knife or the like. Possible surplus is removed.

Application conditions: The product is delivered ready for use.

Optimum temperature for products and surroundings: 18-22 °C  
Do not use at the following temperatures: below 5 ° or above 40 °C

Optimum relative air humidity: Approx. 50 %

System treatment: Primed parts must always be protected with a topcoat treatment before they are exposed to the influence of the weather.

Drying times: Dry to recoat: approx. ½ hour  
Thoroughly dry: approx. 5 mm in 7 days

The drying times are approximate and may vary according to wood quality, temperatures, humidity, ventilation and film thickness.

Cleaning: The equipment is cleaned with water.

**HEALTH AND SAFETY** See Safety Data Sheet.

---

**TECHNICAL DATA SHEET**

6 16.11.2015

Page 2 of 2

**TEKNOSEAL 4001-00**

---

**ADDITIONAL INFORMATION**

Pack size: 250 ml plastic bottle and 310 ml cartridge

Storage: The product must be stored at temperatures above 5 °C. Shelf life 12 months from production date in unopened containers. Keep containers tightly closed after use.

The above information is normative and based on laboratory tests and practical experiences. The information is noncommittal, and we cannot accept liability for the results obtained under working conditions beyond our control, and consequently the buyer or the user is not released from the obligation to test the suitability of our products for specific means and application methods under the actual application conditions. Our liability covers only damage caused directly by defects in the products supplied by Teknos. The latest versions of Teknos' Technical Data Sheets and Safety Data Sheets are available from our homepage [www.teknos.com](http://www.teknos.com).