

Product Datasheet



AkzoNobel
Tomorrow's Answers Today

BU Powder Coatings Chrome Silver MW031D

Product Description

Interpon 310 Chrome Silver is a bright metallic powder with a chrome finish. **Interpon 310** is designed for the interior decoration of all items which require an excellent chrome effect finish such as metal furniture, shop fittings, shelves and light fittings..

Interpon 310 Chrome Silver is a polyester resin based thermo-setting powder coating formulated without TGIC. The product is warning label free.

Interpon 310 Chrome Silver is intended for interior use only when applied as a single coat. For exterior environments or aggressive interior environments Chrome Silver should be over-coated with the acrylic clearcoat **Interpon 410 CZ001D** or with the liquid Topcoat 800 clearcoat form Cromadex. Other clear powder coatings such as epoxy-polyester, polyester or polyurethane are not suitable and will not give the same appearance.

Powder Properties

Chemical type	Polyester
Storage	Dry cool conditions
Shelf life	Under dry, cool (<25°C) conditions 6 months from delivery date
Stoving schedule (object temperature)	at 180°C : min. 15 min. – max. 30 min. at 190°C : min. 10 min. – max. 25 min. at 200°C : min. 6 min. – max. 20 min.
	Failure to observe the correct curing conditions may cause difference in colour, gloss and the deterioration of the coating properties.

Coating

Aspect	Chrome finish	
Test Conditions	The results shown are based on tests which (unless otherwise indicated) have been carried out under laboratory conditions and are given for advice only, actual performance depends upon the circumstances under which the product is used.	
Substrate	0.5 mm steel	
Pre-treatment	Iron phosphate (e. g. Bonder LH 60 OC)	
System	Single coat	2 layer system
First layer	MW031D - 80 µm	MW031D - 80 µm
Curing	15 min - 180°C	15 min - 180°C
Second layer		CZ001D - 80 µm
Curing		20 min - 170°C
Mechanical tests		
Flexibility ISO 1519	6 mm	6 mm
Adhesion ISO 2409	class 0	class 0
Impact ISO 6272-1	1kg 0.5m	N.A.
Erichsen Cupping ISO 1520	> 6 mm	> 6 mm
Durability and chemical tests		
Salt spray test ISO 9227	240 h < 2 mm from scribe - class 0 loss of chrome effect	240 h < 2 mm from scribe class 0 no change of visual aspect
Humidity test ISO 6270-2	240 h no blistering or loss of chrome effect	240 h no change of visual aspect
Exterior durability Florida Natural testing	Interior use only	>50% gloss retention after 24 months
Chemical resistance	See Post Application	

Chrome Silver 2 MW031D

Industrial application conditions

Pre-treatment

Aluminium, steel or Zintec surfaces must be clean and free from grease.

Iron phosphate and lightweight zinc phosphating of ferrous metals improves corrosion resistance.

Aluminium surfaces may require a suitable chromate conversion, chrome free pre-treatment or flash anodising for certain applications.

Galvanised steel may require zinc or chromate conversion or sweep blasting.

Detailed advice should be sought from the pre-treatment supplier

Recommended film thickness

Smooth	:	60 - 80 microns
Fine Structure	:	60 - 90 microns
Coarse Structure	:	80 - 100 microns

Application

Interpon 310 powder coatings can be applied by corona electrostatic or tribostatic equipment.

However the aspect obtained by tribostatic equipment may vary when compared to electrostatic application and/or our colour card.

In all application processes the aspect obtained is subject to variation, depending on the method of application (type of gun, nozzle, pot etc) and the shape/type of component.

We recommend that the actual application parameters are adapted and adjusted depending on the type of component and with each powder batch in order to give a finish in accordance with our colour card.

The following procedure is given as a guideline when using these finishes :

We recommend the use of flat jet spray nozzles.

To ensure powder homogeneity empty the boxes totally into the tray or feed hopper.

Only one spray run and one batch of powder should be used for components which are to be used in the same project.

For manual application it is essential to ensure that an even film thickness is applied and in all instances sinusoidal gun movements should be avoided.

Recycling

Depending of the product - Consult Technical Support of AkzoNobel

Post Application

Contact with Chemical Agents

Contact, even of a short duration with certain household products and chemicals, can cause irreversible changes in the gloss and appearance. We recommend that a test is carried out on a non-visible area before using these types of products on these coatings.

Exposure to aggressive Environments

Due to the high level of metallic particles some finishes are sensitive to aggressive environments (i.e. humid, or areas in which wear by rubbing occurs).

For protection overcoating with a clear coat is recommended.

When using a topcoat the application should be done immediately on the same site.

The maximum allowable period between coats is 2 hours.

For further information please contact AkzoNobel.

Safety Precautions

Please consult the Material Safety Datasheet (MSDS)

FOR PROFESSIONAL USE ONLY

IMPORTANT NOTE The information in this data sheet is not intended to be exhaustive and is based on the present state of our knowledge and on current laws: any person using the product for any purpose other than that specifically recommended in the technical data sheet without first obtaining written confirmation from us as to the suitability of the product for the intended purpose does so at his own risk. It is always the responsibility of the user to take all necessary steps to fulfill the demands set out in the local rules and legislation. Always read the Material Data Sheet and the Technical Data Sheet for this product if available. All advice we give or any statement made about the product by us (whether in this data sheet or otherwise) is correct to the best of our knowledge but we have no control over the quality or the condition of the substrate or the many factors affecting the use and application of the product. Therefore, unless we specifically agree in writing otherwise, we do not accept any liability whatsoever for the performance of the product or for any loss or damage arising out of the use of the product. All products supplied and technical advice given are subject to our standard terms and conditions of sale. You should request a copy of this document and review it carefully. The information contained in this data sheet is subject to modification from time to time in the light of experience and our policy of continuous development. It is the user's responsibility to verify that this data sheet is current prior to using the product.

Brand names mentioned in this data sheet are trademarks of or are licensed to AkzoNobel