



Technical Data



		Standard	Result	Slip Resistance	
				Product	Oil-Wet Ramp
	Size		See separate table	VG5-7LLST	1050 X 250 R10
	Thickness		4.5 mm	VGW33T-7LLST	1050 X 250 R10
	Wear Layer		0.5 mm	VGW38T-7LLST	1050 X 250 R10
	Backing		PVC Friction Pad	VGW39T-7LLST	1050 X 250 R10
	K-Guard Plus		Yes	VGW91T-7LLST	1050 X 250 R10
	Box quantity		12 Planks / 3.15 m²	VGW92T-7LLST	1050 X 250 R10
			10 Tiles / 3.05 m²	LLT200	610 X 500 R9
	Warranty	Commercial	10-Years Wear*	LLT201	610 X 500 R9
		Residential	Limited Lifetime Wear*	LLT202	610 X 500 R9
	Bevelled Edge		No	LLT203	610 X 500 R9
	Standards	EN 649	Pass	LLP93	1050 X 250 R10
		ASTM F1700	Pass	LLP94	1050 X 250 R10
	Classification		Commercial Heavy Duty use	LLP95	1050 X 250 R10
			Domestic Heavy Duty use	LLP96	1050 X 250 R10
	Staining Resistance	EN 423	Class 0	LLP97	1050 X 250 R10
		ASTM F925	Pass	LLP99	1050 X 250 R10
	Colour Fastness to Light	ISO 105-B02	≥7	LLT204	610 X 500 R9
		ASTM F1515	<8	LLT205	610 X 500 R9
	Abrasion Resistance	EN 660-2	Group T	LLT206	610 X 500 R9
		ASTM D3884	Pass	LLT207	610 X 500 R9
	Dimensional stability	EN 434	≤ 0.10%		
		ASTM F2199	Pass		
	Acoustic Impact noise reduction	ISO 140-6 Normalized Impact Sound Insulation L' n, w (C1) 59dB			
		ISO 140-8 Improved Impact Sound Insulation	ΔL _w = 14dB		
		ASTM E492-09 Impact Insulation Class	IIC 56dB		
		Suitable for use on upper floors of residential high-rise apartment buildings without the need for a separate acoustic underlay.			
	Electrical behaviour body voltage	EN 1815	Pass		
		AATCC 134-1996	Pass		
	Indentation - residual	EN 433	≤ 0.1mm		
		ASTM F1914	<8%		
	Castor chair continuous use	EN 425	Pass		
	Thermal conductivity	ISO 8302	0.0245 m²K/W		
			Suitable for underfloor heating		
	Reaction to Fire	AS NZS ISO 9239.1:2003	CRF:	Smoke value:	
			Plank 8.0 kW/m²	105% min	
			Tile 9.4 kW/m²	164% min	
	Slip resistance	AS/NZS 4586:2004	See separate table		
	Adhesive		Please refer to our installation instructions.		
	Recycling		Suitable		

*Full details of the terms and conditions of the Karndean Looselay residential limited and commercial wear guarantees are available by contacting Karndean International. Freecall: 1800 428 963 Fax: 1800 431 048 or Email: customerservice@karndean.com.au.

For more information:
Australia
Call: 1800 33 11 70
Email: customerservice@karndean.com.au
Visit: www.karndean.com

New Zealand
Call: 0800 44 21 01
Email: customerservice@karndean.co.nz
Visit: www.karndean.com

