

	Standard	Result	Product	Size (mm)	Slip Resistance Oil-Wet Ramp
Size		See separate table	AP01	228 X 76	R10
Thickness		3.0 mm	AP02	228 X 76	R10
Wear Layer		0.7 mm	AP03	228 X 76	R10
Warranty	Commercial	15 years*	EW01	915 X 152	R10
	Domestic	20 years*	EW02	915 X 152	R10
Bevelled Edge		Yes	EW03	915 X 152	R10
Standards	EN 649	Pass	HC01	915 X 152	R9
	ASTM F1700	Pass	HC02	915 X 152	R9
Classification		Commercial Heavy Duty use	HC03	915 X 152	R9
		Domestic Extra Heavy Duty use	HC04	915 X 152	R9
Staining Resistance	EN 423	Class 0	HC05	915 X 152	R9
	ASTM F925	Pass	HC06	915 X 152	R9
Colour Fastness to Light	ISO 105-B02	≥6	RL01	1219 X 178	R9
	ASTM F1515	<8	RL02	1219 X 178	R9
Abrasion Resistance	EN 660-2	Group T	RL03	1219 X 178	R9
	ASTM D3884	Pass	RL04	1219 X 178	R9
Dimensional stability	EN 434	≤ 0.25%			
	ASTM F2199	Pass			
Acoustic impact noise reduction	EN ISO 717-2 / EN ISO 140-8	ΔL <sub>w</sub> = 2 db <sup>1</sup>			
Electrical behaviour body voltage	EN 1815	Pass			
Indentation - residual	EN 433	≤ 0.1mm			
	ASTM F1914	<8%			
Castor chair continuous use	EN 425	Pass			
Thermal conductivity	ISO 8302	0.0147 m <sup>2</sup> K/W			
		Suitable for underfloor heating			
Reaction to Fire	AS NZS ISO 9239.1:2003	CRF: Smoke value:			
		Hand Crafted Wood	9.6 kW/m <sup>2</sup>	151% min	
		Oak Royale	10.5 kW/m <sup>2</sup>	48% min	
		Oak Premier	8.5kW/m <sup>2</sup>	177% min	
		Parquet	8.5kW/m <sup>2</sup>	220% min	
Slip resistance	AS/NZS 4586:2004	See separate table			
Adhesive	General use:	Karndean Mega-Bond			
	High temperature:	Karndean 8000 2-part Polyurethane			
Recycling		Suitable			

\*Subject to terms

<sup>1</sup>Result is Ln,w + C<sup>1</sup> = 57 dB when installed on Regupol 4515 acoustic underlay

For more information:

**Australia**

Call: 1800 33 11 70

Email: customerservice@karndean.com.au

Visit: www.karndean.com

**New Zealand**

Call: 0800 44 21 01

Email: customerservice@karndean.co.nz

Visit: www.karndean.com



green building council australia  
MEMBER 2013-2014



	Standard	Result	Product	Size (mm)	Slip Resistance Oil-Wet Ramp
Size		See separate table	CC01	406 X 406	R10
Thickness		3.0 mm	CC02	406 X 406	R10
Wear Layer		0.7 mm	CC03	406 X 406	R10
Warranty	Commercial	15 years*	CC04	406 X 406	R10
	Domestic	20 years*	CC06	406 X 406	R10
Bevelled Edge		Yes	CC08	406 X 406	R10
Standards	EN 649	Pass	CER01	305 X 305	R9
	ASTM F1700	Pass	CK21	406 X 406	R10
Classification		Commercial Heavy Duty use	CK22	406 X 406	R10
		Domestic Extra Heavy Duty use	CK23	406 X 406	R10
			CK24	406 X 406	R10
Staining Resistance	EN 423	Class 0	CK25	406 X 406	R10
	ASTM F925	Pass	CK26	406 X 406	R10
Colour Fastness to Light	ISO 105-B02	≥6	LST01	406 X 406	R9
	ASTM F1515	<8	M45	457 X 305	R9
Abrasion Resistance	EN 660-2	Group T	M45-12	305 X 305	R9
	ASTM D3884	Pass	RP02	915 X 76	R9
Dimensional stability	EN 434	≤ 0.25%	RP11	915 X 76	R9
	ASTM F2199	Pass	RP12	915 X 76	R9
Acoustic impact noise reduction	EN ISO 717-2 / EN ISO 140-8	$\Delta L_w = 2 \text{ db}^1$	RP13	915 X 76	R9
Electrical behaviour body voltage	EN 1815	Pass	RP31	915 X 76	R9
Indentation - residual	EN 433	≤ 0.1mm	RP32	915 X 76	R9
	ASTM F1914	<8%	RP33	915 X 76	R9
Castor chair continuous use	EN 425	Pass	RP41	915 X 76	R9
Thermal conductivity	ISO 8302	0.0147 m <sup>2</sup> K/W	RP61	915 X 76	R9
		Suitable for underfloor heating	RP71	Random width	R9
Reaction to Fire	AS NZS ISO 9239.1:2003	CRF: 9.5 kW/m <sup>2</sup>	RP73	915 X 76	R9
		Smoke value: 82% min.	RP74	915 X 76	R9
Slip resistance	AS/NZS 4586:2004	See separate table	RP75	915 X 76	R9
Adhesive	General use:	Karndean Mega-Bond	SS 6	305 X 305	R9
	High temperature:	Karndean 8000 2-part Polyurethane	TV72	305 X 305	R10
Recycling		Suitable	TV77	305 X 305	R10

\*Subject to terms

<sup>1</sup>Result is  $L_n, w + C^1 = 57 \text{ dB}$  when installed on Regupol 4515 acoustic underlay

For more information:

Australia

Call: 1800 33 11 70

Email: [customerservice@karndean.com.au](mailto:customerservice@karndean.com.au)

Visit: [www.karndean.com](http://www.karndean.com)

New Zealand

Call: 0800 44 21 01

Email: [customerservice@karndean.co.nz](mailto:customerservice@karndean.co.nz)

Visit: [www.karndean.com](http://www.karndean.com)



green building council australia  
MEMBER 2013-2014



	Standard	Result	Product	Size (mm)	Slip Resistance Oil-Wet Ramp
Size		See separate table	VG 1-7	1219 X 178	R10
Thickness		3.0 mm	VG 5-7	1219 X 178	R10
Wear Layer		0.5 mm	VGW33T-7	1219 X 178	R10
Warranty	Commercial	10 years*	VGW39T-7	1219 X 178	R10
	Domestic	15 years*	VGW40T-7	1219 X 178	R10
Bevelled Edge		No	VGW41T-7	1219 X 178	R10
Standards	EN 649	Pass	VGW42T-7	1219 X 178	R10
	ASTM F1700	Pass	VGW44T-7	1219 X 178	R10
Classification		Commercial Heavy Duty use	VGW49T-7	1219 X 178	R10
		Domestic Heavy Duty use	VGW53T-7	1219 X 178	R10
Staining Resistance	EN 423	Class 0	VGW54T-7	1219 X 178	R10
	ASTM F925	Pass	VGW70T-7	1219 X 178	R10
Colour Fastness to Light	ISO 105-B02	≥7	VGW71T-7	1219 X 178	R10
	ASTM F1515	<8	VGW80T-7	1219 X 178	R10
Abrasion Resistance	EN 660-2	Group T	VGW81T-7	1219 X 178	R10
	ASTM D3884	Pass	VGW83T-7	1219 X 178	R10
Dimensional stability	EN 434	≤ 0.25%	VGW84T-7	1219 X 178	R10
	ASTM F2199	Pass	VGW86T-7	1219 X 178	R10
Acoustic Impact noise reduction	EN ISO 717-2 / EN ISO 140-8	ΔL <sub>w</sub> = 4 db <sup>1</sup>	VGW87T-7	1219 X 178	R10
Electrical behaviour body voltage	EN 1815	Pass	VGW88T-7	1219 X 178	R10
Indentation - residual	EN 433	≤ 0.1mm	VGW89T-7	1219 X 178	R10
	ASTM F1914	<8%			
Castor chair continuous use	EN 425	Pass			
Thermal conductivity	ISO 8302	0.0147 m <sup>2</sup> K/W			
		Suitable for underfloor heating			
Reaction to Fire	AS NZS ISO 9239.1:2003	CRF: 9.4 kW/m <sup>2</sup>			
		Smoke value: 84% min.			
Slip resistance	AS/NZS 4586:2004	See separate table			
Adhesive	General use:	Karndean Mega-Bond			
	High temperature:	Karndean 8000 2-part Polyurethane			
Recycling		Suitable			

\*Subject to terms

<sup>1</sup>Result is Ln,w + C<sup>1</sup> = 57 dB when installed on Regupol 4515 acoustic underlay

For more information:

**Australia**

Call: 1800 33 11 70

Email: [customerservice@karndean.com.au](mailto:customerservice@karndean.com.au)

Visit: [www.karndean.com](http://www.karndean.com)

**New Zealand**

Call: 0800 44 21 01


Email: [customerservice@karndean.co.nz](mailto:customerservice@karndean.co.nz)

Visit: [www.karndean.com](http://www.karndean.com)



green building council australia  
MEMBER 2013-2014





# Technical Data



	Standard	Result	Product	Size (mm)	Slip Resistance Oil-Wet Ramp
Size		See separate table	SP111	457 X 457	R10
Thickness		2.5 mm	SP112	457 X 457	R10
Wear Layer		0.5 mm	SP113	457 X 457	R10
Warranty	Commercial	10 years*	SP114	457 X 457	R10
	Domestic	15 years*	SP115	457 X 457	R10
Bevelled Edge		No	SP211	610 X 457	R10
Standards	EN 649	Pass	SP212	610 X 457	R10
	ASTM F1700	Pass	SP213	610 X 457	R10
Classification		Commercial Heavy Duty use	SP214	610 X 457	R10
		Domestic Heavy Duty use	SP215	610 X 457	R10
Staining Resistance	EN 423	Class 0	WP311	915 X 152	R10
	ASTM F925	Pass	WP312	915 X 152	R10
Colour Fastness to Light	ISO 105-B02	≥7	WP313	915 X 152	R10
	ASTM F1515	<8	WP314	915 X 152	R10
Abrasion Resistance	EN 660-2	Group T	WP315	915 X 152	R10
	ASTM D3884	Pass	WP316	915 X 152	R10
Dimensional stability	EN 434	≤ 0.25%	WP317	915 X 152	R10
	ASTM F2199	Pass	WP318	915 X 152	R10
Acoustic Impact noise reduction	EN ISO 717-2 / EN ISO 140-8	ΔL <sub>w</sub> = 2 db <sup>1</sup>	WP319	915 X 152	R10
Electrical behaviour body voltage	EN 1815	Pass	WP411	1219 X 228	R10
Indentation - residual	EN 433	≤ 0.1mm	WP412	1219 X 228	R10
	ASTM F1914	<8%	WP413	1219 X 228	R10
Castor chair continuous use	EN 425	Pass	WP414	1219 X 228	R10
Thermal conductivity	ISO 8302	0.0120 m <sup>2</sup> K/W	WP511	915 X 102	R10
		Suitable for underfloor heating			
Reaction to Fire	AS NZS ISO 9239.1:2003	CRF: 9.1 kW/m <sup>2</sup>			
		Smoke value: 62% min.			
Slip resistance	AS/NZS 4586:2004	See separate table			
Adhesive	General use:	Karndean Mega-Bond			
	High temperature:	Karndean 8000 2-part Polyurethane			
Recycling		Suitable			

\*Subject to terms

<sup>1</sup>Result is Ln,w + C<sup>1</sup> = 57 dB when installed on Regupol 4515 acoustic underlay

For more information:

Australia

Call: 1800 33 11 70

Email: [customerservice@karndean.com.au](mailto:customerservice@karndean.com.au)

Visit: [www.karndean.com](http://www.karndean.com)

New Zealand

Call: 0800 44 21 01




















Email: [customerservice@karndean.co.nz](mailto:customerservice@karndean.co.nz)

Visit: [www.karndean.com](http://www.karndean.com)



green building council australia  
MEMBER 2013-2014



	Standard	Result	Product	Size (mm)	Slip Resistance Oil-Wet Ramp
 Size		See separate table	MLC01	406 X 406	R9
 Thickness		2.5 mm	MLC07	406 X 406	R9
 Wear Layer		0.5 mm	MLC08	406 X 406	R9
Warranty	Commercial	10 years*	MS 1	305 X 305	R9
	Domestic	15 years*	MS 2	305 X 305	R9
 Bevelled Edge		No	MS 3	305 X 305	R9
 Standards	EN 649	Pass	MS 4	305 X 305	R9
	ASTM F1700	Pass	MX92	305 X 305	R10
 Classification		Commercial Heavy Duty use	MX93	305 X 305	R10
		Domestic Heavy Duty use	MX94	305 X 305	R10
 Staining Resistance	EN 423	Class 0	MX95	305 X 305	R10
	ASTM F925	Pass	MX96	305 X 305	R10
 Colour Fastness to Light	ISO 105-B02	≥6	MX97	305 X 305	R10
	ASTM F1515	<8	MX98	305 X 305	R10
 Abrasion Resistance	EN 660-2	Group T	MX99	305 X 305	R10
	ASTM D3884	Pass			
 Dimensional stability	EN 434	≤ 0.25%			
	ASTM F2199	Pass			
 Acoustic Impact noise reduction	EN ISO 717-2 / EN ISO 140-8	ΔL <sub>w</sub> = 2 db <sup>1</sup>			
 Electrical behaviour body voltage	EN 1815	Pass			
 Indentation - residual	EN 433	≤ 0.1mm			
	ASTM F1914	<8%			
 Castor chair continuous use	EN 425	Pass			
 Thermal conductivity	ISO 8302	0.0120 m <sup>2</sup> /K/W			
		Suitable for underfloor heating			
 Reaction to Fire	AS NZS ISO 9239.1:2003	CRF: 9.4 kW/m <sup>2</sup>			
		Smoke value: 58% min.			
 Slip resistance	AS/NZS 4586:2004	See separate table			
 Adhesive	General use:	Karndean Mega-Bond			
	High temperature:	Karndean 8000 2-part Polyurethane			
 Recycling		Suitable			

\*Subject to terms

<sup>1</sup>Result is Ln,w + C<sup>1</sup> = 57 dB when installed on Regupol 4515 acoustic underlay


For more information:  
**Australia**  
 Call: 1800 33 11 70  
 Email: customerservice@karndean.com.au  
 Visit: www.karndean.com

**New Zealand**  
 Call: 0800 44 21 01  
 Email: customerservice@karndean.co.nz  
 Visit: www.karndean.com



green building council australia  
 MEMBER 2013-2014





# Technical Data



	Standard	Result	Product	Size (mm)	Slip Resistance Oil-Wet Ramp
Size		See separate table	KP101	915 X 152	R10
Thickness		2.0 mm	KP103	915 X 152	R10
Wear Layer		0.3 mm	KP104	915 X 152	R10
Warranty	Commercial	10 years*	KP107	915 X 102	R10
	Domestic	12 years*	KP37	915 X 102	R10
Bevelled Edge		No	KP39	915 X 102	R10
Standards	EN 649	Pass	KP54-6	915 X 152	R10
	ASTM F1700	Pass	KP55-6	915 X 152	R10
Classification		Commercial Light Duty use	KP91	915 X 102	R10
		Domestic Heavy Duty use	KP94	915 X 152	R10
Staining Resistance	EN 423	Class 0	KP95	915 X 152	R10
	ASTM F925	Pass	KP96	915 X 152	R10
Colour Fastness to Light	ISO 105-B02	≥6	KP97	915 X 152	R10
	ASTM F1515	<8	KP98	915 X 152	R10
Abrasion Resistance	EN 660-2	Group T	ST 5-18	457 X 305	R10
	ASTM D3884	Pass	ST 8	305 X 305	R10
Dimensional stability	EN 434	≤ 0.25%	ST 9	305 X 305	R10
	ASTM F2199	Pass	ST11	457 X 305	R9
Acoustic Impact noise reduction	EN ISO 717-2 / EN ISO 140-8	$\Delta L_w = 1 \text{ db}^1$	ST12	457 X 305	R9
Electrical behaviour body voltage	EN 1815	Pass	ST13	457 X 305	R9
Indentation - residual	EN 433	≤ 0.1mm	ST14	457 X 305	R9
	ASTM F1914	<8%	T100	305 X 305	R10
Castor chair continuous use	EN 425	Pass	T88	305 X 305	R10
Thermal conductivity	ISO 8302	0.0100 m <sup>2</sup> K/W	T89	305 X 305	R10
		Suitable for underfloor heating	T98	305 X 305	R10
Reaction to Fire	AS NZS ISO 9239.1:2003	CRF: 8.6 kW/m <sup>2</sup>	T99-18	457 X 305	R10
		Smoke value: 56% min.			
Slip resistance	AS/NZS 4586:2004	See separate table			
Adhesive	General use:	Karndean Mega-Bond			
	High temperature:	Karndean 8000 2-part Polyurethane			
Recycling		Suitable			

\*Subject to terms

<sup>1</sup>Result is  $L_n, w + C^1 = 57 \text{ dB}$  when installed on Regupol 4515 acoustic underlay

For more information:

**Australia**  
 Call: 1800 33 11 70  
 Email: customerservice@karndean.com.au  
 Visit: www.karndean.com

**New Zealand**  
 Call: 0800 44 21 01  
 Email: customerservice@karndean.co.nz  
 Visit: www.karndean.com

